

Sontex Machinery Limited

Unit B1 Cartwright Street Cleckheaton BD19 5LY

SHRINKABLE PVC FILM - MONOFOLDED - our type TERMOPACK

Properties	Method	Condition	Unit		Value	Value	Value	Tolerance
------------	--------	-----------	------	--	-------	-------	-------	-----------

Physical Characteristics

Specific Weight			g/m ²		1,32	1,32	1,32	
Thickness			micron		17	24	38	
Grammage			g/m ²		22,4	31,7	50,2	± 10 %

Mechanical Characteristics

Tensile Strength	ASTM D882		N/mm ²	MD	60	60	65	± 10 %
				TD	50	55	55	
Elongation at break	ASTM D882		%	MD	120	140	140	± 10 %
				TD	150	170	170	
Shrinkage			%		40/40	40/40	40/40	
Heat seal strength *			°C		150	150	150	7%

Notes

*= it indicates unusual tests

MD= longitudinal way TD= trasverse way

Other Information

Hygiene and Safety Regulation See Our Safety Data Sheet

Storage Conditions and Shelf Life:

Store our product in a cool, dry and well ventilated area. Avoid direct sunlight.

If properly stored, our product can be used for the following 3 months after its production.

The above technical information is based on statistical analyses drawn from numerous data. In any case, no guarantee is provided on the results of these analyses.

The users are recommended to carry out their own tests to determine the usefulness of this product according to its purpose.